

Plastazote (LD29)



- PE foam "Plastazote"
- Sheet Size: 200 x 100 cm
- Self adhesive also available

PROPERTIES	AVERAGE VALUE
Density	29kg m ³
Shore Hardness 00 Scale	53
Compression set 25% comp 22hr 23 deg C ½ hr recovery 24 hr recovery	10.5% 3%
Compression Set 50% comp 22hr 23 deg C ½ hr recovery 24 recovery	23.5% 14%
Tensile Elongation	140 %
Operating Temperature	- 70°C / + 100°C
Tensile Strength	375 kPa
Tear Strength	740 N/m
Horizontal Burning Characteristics Automotive FMVSS 302 – Burn rate	Pass 8mm and thicker
Horizontal Burn Rate 5mm thick 13mm thick	1.7 mm/sec 1.2 mm/sec



2987/05	Thickness 5 mm
2987/10	Thickness 10 mm
2987/15	Thickness 15 mm
2987/20	Thickness 20 mm
2987/30	Thickness 30 mm
2987/40	Thickness 40 mm
2987/50	Thickness 50 mm
2987/60	Thickness 60 mm
2987/70	Thickness 70 mm
2987/80	Thickness 80 mm
2987/90	Thickness 90 mm
2987/100	Thickness 100 mm